Insulated Glass Units-Double Silver Low-E Coating

Glass makeup	Reflective colour	Visible Light(%)			Solar Engergy(%)		U-Value ($W/m^2.K$)		SC	SHGC
		Trans	Refl.		Trans	Refl.				
			Outer	Inner		Outer	Summer	Winter		
6SDF146 II coating on Clear+12A+6C	Blue	41	13	19	17	27	1.61	1.66	0.29	0.25
6SDF156 II coating on Clear+12A+6C	Blue green	51	15	19	24	32	1.54	1.61	0.32	0.28
6SDF163 II coating on Clear+12A+6C	Light blue green	58	15	16	30	28	1.60	1.65	0.38	0.33
6SDF176 II coating on Clear+12A+6C	Neutral	68	11	12	39	27	1.58	1.64	0.45	0.39
6SDF346 II coating on Euro grey+12A+6C	Grey	20	8	18	9	26	1.62	1.67	0.19	0.16
6SDF356 II coating on Euro grey+12A+6C	Grey	24	8	19	12	14	1.55	1.61	0.20	0.17
6SDF363 II coating on Euro grey+12A+6C	Grey	27	7	15	17	10	1.62	1.66	0.24	0.21
6SDF376 II coating on Euro grey+12A+6C	Grey	33	6	10	19	13	1.59	1.64	0.28	0.25
6SDF446 II coating on Green+12A+6C	Green	34	11	19	13	26	1.61	1.67	0.23	0.20
6SDF456 II coating on Green+12A+6C	Green	41	13	19	15	11	1.61	1.66	0.26	0.22
6SDF463 II coating on Green+12A+6C	Light blue green	48	12	15	21	9	1.62	1.66	0.29	0.26
6SDF476 II coating on Green+12A+6C	Light green	56	9	11	26	8	1.59	1.64	0.33	0.29
6SDF546 II coating on Crystal grey+12A+6C	Grey	29	13	18	13	25	1.62	1.67	0.23	0.20
6SDF556 II coating on Crystal grey+12A+6C	Grey	35	15	18	17	31	1.55	1.61	0.29	0.25
6SDF563 II coating on Crystal grey+12A+6C	Light Grey	41	10	14	22	26	1.62	1.66	0.34	0.30
6SDF576 II coating on Crystal grey+12A+6C	Light Grey	48	8	10	28	23	1.59	1.64	0.35	0.30
6SDF746 II coating on Blue+12A+6C	Blue	26	11	18	13	11	1.61	1.66	0.21	0.18
6SDF756 II coating on Blue+12A+6C	Blue	32	10	19	13	11	1.56	1.63	0.24	0.20
6SDF763 II coating on Blue+12A+6C	Blue	39	11	11	18	16	1.63	1.64	0.26	0.23
6SDF776 II coating on Blue+12A+6C	Blue	44	8	10	19	12	1.6	1.7	0.30	0.26
6SDF046 II coating on Low-iron+12A+6Low-iron	Light blue	43	13	19	19	27	1.61	1.66	0.30	0.26
6SDF056 II coating on Low-iron+12A+6Low-iron	Blue green	53	15	19	26	32	1.54	1.61	0.33	0.29
6SDF063 II coating on Low-iron+12A+6Low-iron	Light blue green	60	15	17	33	33	1.60	1.65	0.39	0.34
6SDF076 II coating on Low-iron+12A+6Low-iron	Neutral	71	11	12	39	27	1.58	1.64	0.46	0.40