Insulated Glass Units-Single Silver Low-E Coating

Glass makeup	Reflective colour	Visible Light(%)			Solar Engergy(%)		U-Value ($W/m^2.K$)		SC	SHGC
		Trans	Refl.		Trans	Refl.				
			Outer	Inner		Outer	Summer	Winter		
6DF1530 coating on Clear+12A+6C	Silver grey	30	30	10	19	29	1.79	1.80	0.29	0.25
6DF140 coating on Clear+12A+6C	Light grey	37	23	11	23	24	1.80	1.80	0.33	0.28
6DF1548 coating on Clear+12A+6C	Light grey	42	27	18	25	37	1.81	1.81	0.34	0.30
6DF1850 coating on Clear+12A+6C	Silver grey	45	30	16	29	32	1.76	1.77	0.38	0.33
6DF1352 coating on Clear+12A+6C	Blue grey	46	21	10	28	26	1.83	1.84	0.40	0.35
6DF1560 coating on Clear+12A+6C	Light grey	53	19	11	33	25	1.84	1.84	0.44	0.38
6DF164 coating on Clear+12A+6C	Light blue	57	14	10	39	16	1.89	1.88	0.53	0.46
6DF166 coating on Clear+12A+6C	Blue grey	58	19	13	36	26	1.75	1.76	0.48	0.42
6DF1770 coating on Clear+12A+6C	Neutral	60	13	11	37	11	1.70	1.73	0.49	0.43
6DF1580 coating on Clear+12A+6C	Neutral	72	11	12	48	18	1.82	1.82	0.64	0.56
6CL184 coating on Clear +12A+6C	Clear	75	11	11	50	17	1.74	1.76	0.65	0.57
6DF340 coating on Euro grey+12A+6C	Dark Grey	18	9	12	12	11	1.80	1.80	0.21	0.18
6DF3548 coating on Euro grey+12A+6C	Grey	22	10	15	16	14	1.81	1.81	0.22	0.19
6DF3352 coating on Euro grey +12A+6C	Grey	23	7	10	17	9	1.84	1.84	0.27	0.24
6DF3560 coating on Euro grey +12A+6C	Grey	25	8	11	17	11	1.84	1.84	0.27	0.23
6DF366 coating on Euro grey+12A+6C	Grey	28	8	12	19	11	1.75	1.76	0.29	0.25
6CL384 coating on Euro grey+12A+6C	Grey	36	6	10	27	9	1.74	1.76	0.39	0.34
6DF440 coating on Green+12A+6C	Green	30	17	12	15	11	1.80	1.80	0.25	0.21
6DF4548 coating on Green+12A+6C	Green	37	21	16	18	13	1.81	1.81	0.26	0.22
6DF4352 coating on Green+12A+6C	Green	38	11	13	18	8	1.83	1.84	0.28	0.24
6DF4560 coating on Green+12A+6C	Light green	42	14	12	21	10	1.80	1.80	0.33	0.29
6DF466 coating on Green+12A+6C	Light green	48	14	13	23	10	1.75	1.76	0.33	0.29
6CL484 coating on Green+12A+6C	Light green	62	9	10	31	8	1.74	1.76	0.43	0.38
6DF540 coating on Crystal grey+12A+6C	Grey	26	14	12	17	17	1.80	1.80	0.27	0.23
6DF5548 coating on Crystal grey+12A+6C	Silver grey	31	18	16	23	23	1.81	1.81	0.28	0.24
6DF5352 coating on Crystal grey +12A+6C	Grey	32	9	13	22	15	1.83	1.84	0.32	0.28
6DF5560 coating on Crystal grey +12A+6C	Grey	36	11	11	25	17	1.84	1.84	0.35	0.30
6DF566 coating on Crystal grey+12A+6C	Light grey	41	9	10	28	14	1.75	1.76	0.39	0.34
6CL584 coating on Crystal grey+12A+6C	Light grey	53	8	11	39	14	1.74	1.76	0.51	0.45
6DF740 coating on Blue+12A+6C	Blue	24	12	12	14	10	1.80	1.80	0.23	0.20
6DF7548 coating on Blue+12A+6C	Blue	28	14	16	16	11	1.81	1.81	0.23	0.20
6DF7352 coating on Blue+12A+6C	Blue	29	11	10	17	10	1.90	1.88	0.30	0.26
6DF7560 coating on Blue+12A+6C	Blue	33	10	11	19	9	1.84	1.84	0.28	0.25
6DF766 coating on Blue+12A+6C	Blue	38	8	10	30	9	1.75	1.76	0.34	0.30
6CL784 coating on Blue+12A+6C	Light blue	48	7	10	28	8	1.74	1.76	0.38	0.33
6DF040 coating on Low-iron+12A+6Low-iron	Light grey	38	23	12	26	27	1.80	1.80	0.34	0.30
6DF0548 coating on Low-iron+12A+6Low-iron	Light grey	44	27	18	27	37	1.81	1.81	0.35	0.31
6DF0352 coating on Low-iron +12A+6Low-iron	Blue grey	48	21	10	30	26	1.83	1.84	0.41	0.36
6DF0560 coating on Low-iron +12A+6Low-iron	Light grey	53	19	12	37	27	1.84	1.84	0.46	0.40
6DF066 coating on Low-iron+12A+6Low-iron	Light blue	61	20	14	41	26	1.75	1.76	0.50	0.44
6CL084 coating on Low-iron+12A+6Low-iron	Clear	78	12	12	58	22	1.74	1.76	0.79	0.61