Insulated Glass Units-Triple Silver Low-E Coating

Glass makeup	Reflective colour	Visible Light(%)			Solar Engergy(%)		U-Value ($W/m^2.K$)		SC	SHGC
		Trans	Refl.		Trans	Refl.				
			Outer	Inner		Outer	Summer	Winter		
6Sunguard SNX 62/27 coating on Clear+12A+6C	Neutral	61	11	12	23	39	1.56	1.63	0.31	0.27
6Sunguard SNX 62/27 coating on Green+12A+6C	Light green	52	10	11	18	11	1.56	1.63	0.28	0.25
6Sunguard SNX 62/27 coating on Low-iron+12A+6Low-iron	Neutral	64	11	12	24	48	1.56	1.63	0.31	0.27
6Sunguard SNX 62/27 coating on Crystal grey+12A+6C	Light grey	45	8	11	16	19	1.56	1.63	0.26	0.23